

NAUTIX CYCLE

▷ PROPELLERS and Z-DRIVE

ACRALU + PA primer - A7.Speed Antifouling



1) PREPARATION

- Wash the surface and degrease with Nautix **Degreaser**
- Remove old paints and rough sand with 80-120 grit paper
- Rinse with fresh water and let dry thoroughly



Work in a well ventilated area.
Wear appropriate protective clothing, gloves, glasses and mask.

2) ADHESION PRIMER

- Apply 1 thin coat of Nautix **Acralu** adhesion primer.
- Homogenize each part separately before mixing.
- Do mix only the necessary quantity.
- Do not mix with thinner.
- Recommended overcoating time : 30 min




	10°C	15 °C	20°C	25°C
Pot life	9 h	8 h	6 h	3 h
Hand Dry	20 min	15 min	10 min	5 min
Max. overcoating time	2 h	1h30	1 h	30 min

Mixing ratio : 1 for 1 in weight
Covering: 15 m²/L per coat
Cleaning solvent : Nautix **DP**

3) PROTECTION PRIMER

Only for aluminium propellers :

- Apply 3 coats of Nautix **PA** primer



	10°C	15 °C	20°C	30°C
Hand dry	3 h	2 h	1 h 30	30 min
Sandable	24 h	20 h	12 h	6 h
Dry	4 days	3 days	30 h	20 h

Covering : 14 m²/L for 1 coat
Cleaning : Nautix **DP**

4) ANTIFOULING A7T.SPEED

- Apply 4 coats of Nautix **A7T.Speed** antifouling
- Application between 10°C and 35°C.
- To avoid blisters forming with condensation, hull and paint temperature must be close to air temperature.



	10°C	15 °C	20°C	25°C
Hand dry	2 h	3 h	1 h	30 min
Between 2 coats	4 h	3 h	2 h	1 h
Before launching	4 h	3 h	2 h	1 h

Application : brush, spraygun (2 bars–nozzle 1.8 à 2mm)
Covering : 12.5 m²/L per coat



Nautix – Z.I. des 5 chemins
56520 Guidel, France
Tel: +33.(0)2.97.65.32.69
Fax: +33.(0)2.97.65.03.54
info@nautix.com — www.nautix.com